


Description	Latex based emulsion, suitable for interior use.
Typical application	To be applied in a one or two coat system on sufficiently dried out new substrates of concrete, plasterwork, masonry, soft-board, wood fibre. Can also be applied over previously painted washable latex emulsions.
Principle Characteristics	<ul style="list-style-type: none">◆ Non yellowing ;◆ Water resistant; cleanable ;◆ Odourless, rooms painted can be put into use within a few hours.◆ Economical◆ Anti-fungal
Colours	Standard – Sigma Colour Chart
Packing	2.5 Lt, 5 Lt and 10 Lt
Basic Data	
Specific gravity	Approx. 1,52 g/cm ³ (white) Approx. 1,4 g/cm ³ (colours)
Solids content	35,5% vol (white)
Drying time:	Dust dry 30 minutes Recoat after Minimum interval 2-3 hours Maximum interval no limitations
Recommended dry film thickness	35 µm
Shelf life	12 months, if stored in a cool and dry place, in original and closed packing.
Flashpoint	Not applicable, over 65°C
Spreading Rate	
Theoretical	10 m ² /lt
Practical	7-9 m ² /lt but depends on a number of factors such as surface condition and weather condition.

**Substrate Condition**New/ unpainted surfaces

Remove all loose and powdery layers, together with dust and grease. Use a primer if the surface has high or uneven porosity or if heavy pastel shades are to be applied.

Previously treated

1. Distemper.
Remove old distemper completely e.g. by washing off.
2. Emulsion Paint.
Remove all old and blistering paint. The surface should be free from any contamination.

System

A one or two coat system. A wall coating of normal appearance is obtained by thinning down this paint with about 0-15 % water. An attractive finish can be achieved by rolling. In this case, little or no water should be added to the finishing coat.

Instruction for use

	<u>Airless</u>	<u>Airspray</u>	<u>Roller</u>
Thinner	Tap water	Tap water	Tap water
Volume of thinner	0-5 %	10-15 %	0-15 %
Nozzle orifice	0.46-0.53mm	1.5-2mm	
Nozzle pressure	16.5 MPa	0.3-0.4 MPa	

Cleaning solvent

Tap water

Limitation of Liability - The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by Sigma Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

Sigma Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Sigma Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development.

This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.